

FLAMMABILITY TEST REPORT

Report No.: LEI19080829A

Date Received: 06/08/19

Date Tested: 12/08/19

Date Issued: 12/08/19

Company Name & Address: FARGOTEX SP. Z O.O.
AL. LEGIONÓW 114 C
18-400 ŁOMŻA
POLSKA

Contact Name: EWELINA SŁABY

Sample Details:

Reference No.: Not stated
Order No.: Not stated
Style No.: / Batch No.: Rene
Quality: Chenille Fabric
Fabric Colour: Not stated
Manufacturer: Not stated
Supplier: Not stated
Buyer / Retailer: Fargotex
Intended Use: Furniture Fabrics
Quoted Fibre Composition: 100% Polyester
Retailer: Not stated
Specification No.: Not stated
Sample Description: Black and grey coloured woven fabric

| Test Method | Pre Treatment | Requirement | Result |
|--|---------------|---|-----------------|
| BS 5852: Part 1: 1979, Ignition source 0 (Cigarette) | None | Compliance with Schedule 4 Part 1 (The cigarette test) of The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended). | Complies |
| <p>Note: Fabric was submitted for test rather than the upholstery composite so as suggested by The Guide to the Furniture Regulations the cover fabric was tested for cigarette resistance using standard polyurethane foam (non-modified) as this will give the furniture manufacturer a good indication of its likelihood to pass the cigarette test for the finished article</p> | | | |



.....
STEVEN OWEN
(Technical & Operational
Excellence Manager)

.....
ANDREW HALLETT
(Flammability Team Leader)

.....
CAROLE SPOWART
(Flammability
Administrator)

.....
GREGORY JAMES
(Flammability Technician)

Report No.: LEI19080829A Page 1 of 2

FLAMMABILITY TEST REPORT

Test Specification

Test Method: BS 5852: Part 1: 1979 as modified by Schedule 4 Part 1 of the Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended).
Ignition Source: Filterless cigarette
Side Tested: Face

Filling Specification

Filling Type: Polyurethane foam
Supplier / Grade: Carpenter / RP21130 Unmodified
Size: 450 X 300 X 75mm (back) & 450 X 150 X 75mm (seat)
Density / Hardness: 20-22 kg/m³ / Type B, 130N

Pre-treatment / Durability procedure

None

Conditioning

Prior to testing: At least 72 hours in ambient indoor conditions, then at least 16 hours in an atmosphere having a temperature of 20±5°C and a relative humidity of 50±20%
At Time of Testing: Temperature between 15°C & 30°C. Relative humidity between 20% & 70%

Test Results

"The following test results relate only to the ignitability of the combinations of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use."

| | |
|-----------------------------|---|
| Ignition source 0 (Test 1): | The cigarette burnt out within 20 minutes, there was no flaming or progressive smouldering. (Pass) |
| Ignition source 0 (Test 2): | The cigarette burnt out within 21 minutes, there was no flaming or progressive smouldering. (Pass) |

Conclusion

The composite tested meets the requirements of Schedule 4 Part 1 (The cigarette test) of The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended). **PASS.**

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.